

## **Acrylic Resin Based Elastomeric Waterproofing Product**

### **PRODUCT DESCRIPTION**

It is an elastomeric resin-based, single-component, spread-based, ready-to-use, super elastic waterproofing material.

### **FEATURES**

Depends on its elastic structure, it has high resistance to temperature differences.  
It is easy to apply.  
Provides a seamless veneer appearance.  
It has strong penetration.  
It has crack bridging ability.

### **PRODUCT INFORMATION**

Chemical Structure	Acrylic based / Water based
Appearance / Color	Liquid / White
Ph	7-10
Intensity	1,40 ±0,2 g / cm <sup>3</sup>

### **PERFORMANCE**

(23°C, 50% Relative Humidity)

Maximum Pressure 28 days	15 N
Maximum Stretch 28 days	5 N/mm <sup>2</sup>
Adherence (concrete) 28 days	1N/mm <sup>2</sup>
Elongation at break 28 days	%600

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. Values may change as temperature and humidity values in the construction site environment and application surfaces and areas will vary.

### **USAGE AREAS**

On sloping roofs and terraces covered with concrete, plaster or cement board, provided that they are covered.

It is used in under-ceramic waterproofing applications in areas such as bathrooms, kitchens, toilets and shower cabins.

# 301 PROAQUA



## **Acrylic Resin Based Elastomeric Waterproofing Product**

### **APPLICATION INSTRUCTIONS**

The surfaces to be applied must be damp, dry surfaces must be moistened before application. Surface; It must be cured and solid. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. Defects on the surface, areas to be chamfered, gaps and cracks should be repaired with PROREPAIR repair mortar at least 24 hours in advance. Corners and joints should be covered with PROBAND waterproofing chamfer tape.

Curvatures that may cause ponding should be corrected.

We recommend our PROLATEX 710 product for the primer coat.

Or, PROAQUA 301 can be diluted 1/1 with clean water and applied as 1 coat of primer.

For the other 2 coats, PROAQUA is applied undiluted.

### **Application Equipment**

Hand mixer - Roller & Brush

Application should not be made in rainy or humid weather. Make sure that the surface is dry and start the application. For the primer coat, dilute PROAQUA 301.1/1. Otherwise, blistering and poor adherence will occur. The surface is primed in a single layer. It is recommended to apply chamfer tape to corner joints for waterproofing. First of all, it should be applied without diluting with a thin brush to the areas where chamfer tape has been applied. 24 hours after the priming process, a trellising method is applied with a brush or roller without diluting, with the 1st layer applied horizontally and the 2nd layer applied vertically. If necessary, a 3rd layer application can be applied. The total thickness should be 1-2 mm. You should wait 24 hours between coats. If desired, the surface can be sanded before it dries in the final coat application.

### **LIMITATIONS**

To obtain optimum quality, please adhere to the application instructions. Application should not be made in very high temperatures, direct exposure to sunlight, very windy or rainy weather. Application should not be made on surfaces at risk of frost. The application area should not be exposed to excessive load traffic. Application should be made between +5 C and +30 C. Application should never be made at temperatures below 5 C. The product should be protected from rain, water, frost and negative external factors until it is cured.

### **CONSUMPTION**

Approximately 1.5- 2 kg/m<sup>2</sup> on 2 floors

### **PACKAGING**

5kg plastic bucket  
20 kg plastic bucket



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 301 PROAQUA



**Acrylic Resin Based  
Elastomeric Waterproofing Product**

## SHELF LIFE

It is 1 year from the date of production in its original packaging in moisture-free and dry environments (temperature between +5 C and +25 C). The mouth of the containers should be tightly closed when not in use. It should be kept away from moisture.

## STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). It should not be left under direct sunlight.

## SAFETY

Avoid contact with skin and eyes. Use protective gloves, glasses and clothing. In case of eye contact, rinse with plenty of water and consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

## LEGAL NOTES

*Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.*

*DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.*

*DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.*



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE  
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com