

365 PROPOL 2K



Polyurethane Based Double Component Waterproofing Product Suitable for Drinking Water

PRODUCT DESCRIPTION

It is a polyurethane-based, solvent-free, two-component membrane designed for drinking water tanks and applied for waterproofing and protection purposes.

FEATURES

It is suitable for use in drinking water tank insulation. It is solvent-free.

When applied, it creates a one-piece waterproofing layer that prevents the formation of joints or the possibility of leakage.

Since it is a pure polyurethane, it can constantly come into contact with water.

Heat resistance performance in a wide temperature range is between -40° C and +80° C.

Even if the waterproofing layer is damaged in any way, the damaged part can be easily repaired in a short time.

It is resistant to chemicals.

PRODUCT INFORMATION

Chemical Structure Polyurethane
Appearance / Color Liquid / Blue & White & Gray

PERFORMANCE

(23°C, 50% Relative Humidity)

Intensity: 1,35 gr/cm³ ±0.02 ASTM D 1475/EN ISO 2811-1(20° C)
Viscosity: 9000-10000 cp ASTM D 2196/EN ISO 3219(25° C)
Hardness: 40 (Shore D) ASTM 02240
Adhesion to Concrete: < 2 N/mm²ASTM D 903
drying time: 6 Hr
Recoating: 12-24 Hrs
Complete Drying: 7 Days

These values were obtained as a result of laboratory experiments and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

USAGE AREAS

Drinking water tanks, Drinking water distribution channels,
irrigation channels, concrete surfaces, Plaster and cement panels,
It can be used in interior and exterior application areas.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

365 PROPOL 2K



Polyurethane Based Double Component Waterproofing Product Suitable for Drinking Water

APPLICATION INSTRUCTIONS

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. If there are any cracks or breaks on the surface, they should be repaired with PROREPAIR PLUS, PROMORTAR EPO or PROEPO ANCHOR at least 24 hours in advance. Curvatures that may cause ponding should be corrected. The application surface must be flat and without slope.

It is ready for use. Do not add any external substance or dilute it.

Application Equipment

Roller and Brush

The floor must be primed with PROPOL PR, PROPOL or a suitable primer beforehand. It should be applied to the prepared surface with a brush, trowel or spray. By pouring it onto the primed surface or dipping it into a bucket, use a roller or brush until the entire surface is covered, min. It should be applied in two layers. After applying the first coat, min. 8, max. The second coat should be applied within 24 hours. In floor applications, it can be applied in a single layer of 1.40 Kg / m². Waiting time between coats should not exceed 48 hours. Tools used after application should be cleaned within 2 hours.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should not be made when it is raining or when there is a possibility of rain. It should be protected from frost, sun and strong wind for the first 24 hours after application. The application should be made to the part of the structure that comes into contact with water. Since the material will cure slower in cold weather, it should be ensured that the first layer is completely dry before applying the second layer. It is necessary to pay attention to the application temperature and apply within the temperature range of +5°C +30°C.

CONSUMPTION

0.500 - 0.750 Kg/m² for each floor

Total theoretical consumption 1.0 - 1.50 Kg/m²

PACKAGING

A:24 kg B: 4 KG : 28 kg tin packaging

A: 6 kg B: 1 KG : 7 kg tin packaging

SHELF LIFE

It is 1 year from the date of production in its original packaging in moisture-free and dry environments (temperature between +5 C and +25 C). The mouth of the containers should be tightly closed when not in use. It should be kept away from moisture.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

365 PROPOL 2K



Polyurethane Based Double Component Waterproofing Product Suitable for Drinking Water

STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). It should not be left under direct sunlight.

SAFETY

You should not smoke during application and work in well-ventilated environments, away from naked flames. Avoid contact with skin and eyes. Use protective gloves, glasses and clothing. In case of eye contact, rinse with plenty of water and consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com