

201 PROCRYSTA



Cement Based Crystallized Waterproofing Product

PRODUCT DESCRIPTION

It is a single-component, crystalline waterproofing mortar that is cement-based, polymer emulsion reinforced, and contains active chemicals with a crystallizing effect.

FEATURES

- It is suitable for use in drinking water tank insulation.
- It is resistant to hydrostatic pressure.
- The active chemical compound with a crystallizing effect fills the capillary gaps in the concrete.
- It can be applied against negative and positive water pressure.
- It is easy and fast to prepare.
- It can be applied with brush and spray equipment.
- Working time has been extended.
- It provides permanent waterproofing with the crystals it forms.
- It creates a jointless, seamless, permanent, moisture and water-proof waterproofing layer.
- It is resistant to chemicals and salt solutions in the soil.
- Can be applied to damp surface.
- Provides high level of resistance to freeze-thaw cycle.
- Provides negative and positive insulation.
- It is suitable for drinking water use.
- It fills 0.4 mm wide cracks by forming crystals.
- It has a constantly active structure.

PRODUCT INFORMATION

- Chemical Structure : Cement based/containing active chemicals
- Appearance / Color : Powder / Gray

PERFORMANCE

(at 23°C, 50% relative humidity)

Dry Bulk Density	1350 ± 200 kg/m ³	TS EN 1015-10
Coating on	7 Days	
full cure	28 Days	
Pot life	45 Min	

These values were obtained as a result of laboratory experiments carried out in our company at 23°C and 50% relative humidity, and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

201 PROCRYSTA



Cement Based Crystallized Waterproofing Product

USAGE AREAS

In waterproofing of concrete surfaces, In the waterproofing of elevator shafts,
In waterproofing of horizontal and vertical surfaces, Waterproofing from negative and positive sides,
In water tanks, In reinforced concrete pipes, Protecting concrete against water, salt and carbonation,
It is used in the waterproofing of structures above and below ground .

APPLICATION INSTRUCTIONS

The surfaces to be applied must be damp, dry surfaces must be moistened before application. Surface;
It must be cured and solid. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit
that would prevent adhesion. If there is a defect on the surface, PROREPAIR THIN or PROREPAIR; If
application will be made in environments exposed to high sulphate such as sea water and sewage, it
should be repaired with PROREPAIR PLUS at least 24 hours in advance. Corners and joints should be
covered with waterproofing chamfer tape. If there are active water leaks and gaps, they must be filled
with a PROSTOP water plug. The ground should be saturated with water 24 hours before application,
and should be moistened again immediately before application.

Slowly pour 25 kg of powder component into approximately 6 kg of water and mix with a low-speed
mixer until no lumps remain. It is mixed again before application.

Application Equipment

Hand mixer - Brush - Spraying equipment

It is applied with a brush or suitable spray equipment. It should be applied to the surface in 2-3 layers.
The application of each layer should be done in a trellising manner perpendicular to the previous one. At
least 12 hours should be waited between coats. After final drying, the product must be moistened with
water for 5 days. In places with traffic load, a protective layer should be applied. Expired mortar should
be disposed of.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made
between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application
should not be made on surfaces at risk of frost. The product should be protected from rain, water, frost
and negative external factors until it is cured.

CONSUMPTION

2 kg /m² depending on water pressure .



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

201 PROCRYSTA



Cement Based Crystallized Waterproofing Product

SAFETY

Since it is cement based, do not breathe the dust, use a mask. Avoid contact with skin and eyes. Use protective gloves, glasses and clothing. In case of eye contact, rinse with plenty of water and consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com