

980 PROTHERM PRIMER



Interior and Exterior Paint Primer

PRODUCT DESCRIPTION

It is a water-based, acrylic emulsion-based interior and exterior paint primer.

FEATURES

It is used as a first coat primer on plaster and concrete-like surfaces .

Reduces the consumption of topcoat paints.

Prepares a healthy ground.

It has high adherence .

It can be used easily on old painted exterior surfaces .

Easy to apply .

It is environmentally friendly .

PRODUCT INFORMATION

Chemical structure	Styrene Acrylic based / Water based
Appearance/Color	Liquid / White
Ph	7-10
Intensity	1,30±0,2g/cm ³

PERFORMANCE

(23°C, 50% Relative Humidity)

Brightness	G3	TS 4318 EN ISO 2813
Grain Size	S1	TS 2620 EN ISO 1524

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

USAGE AREAS

On exterior facades; It is used before painting on surfaces such as concrete, brick, cement-based plaster, aerated concrete, etc.

APPLICATION INSTRUCTIONS

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. The surface should be rough. If there are significant defects on the application surface, they should be repaired with PROREPAIR repair mortar .

PROTHERM PRIMER Exterior primer is ready to use. 10% water can be added if desired. It is mixed with a low speed mixer.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

980 PROTHERM PRIMER



Interior and Exterior Paint Primer

Application Equipment

hand mixer - Roll

The prepared mixture is applied to the surface preparation area with a clean roller.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application should not be made on surfaces at risk of frost. The product should be protected from rain, water, frost and negative external factors until it is cured.

CONSUMPTION

10-12 m² / lt in a single coat, depending on the absorbency of the surface

PACKAGING

15 lt plastik bucket

SHELF LIFE

It is valid for 1 year from the date of production in its original packaging with the lid closed, in a moisture-free and dry environment away from direct sunlight, at a temperature of +5 - 25 C and 50% relative humidity. The lids of the packages should be closed tightly when not in use. It should be kept away from moisture. Protect from high temperatures and frost.

STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). It should not be left under direct sunlight.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

980 PROTHERM PRIMER



Interior and Exterior Paint Primer

SAFETY

Do not inhale, avoid contact with skin and eyes. Use protective gloves, glasses and clothing. In case of eye contact, rinse with plenty of water and consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet. .

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com