

Silicone Exterior Paint

PRODUCT DESCRIPTION

It is a water-based, acrylic emulsion-based, silicone-reinforced topcoat exterior paint.

FEATURES

It has high covering power.
It has high adherence.
It is resistant to rain.
It is matte.
Easy to apply.
It is environmentally friendly.

PRODUCT INFORMATION

| | |
|--------------------|-------------------------------------|
| Chemical structure | Styrene Acrylic based / Water based |
| Appearance/Color | Liquid / Desired |
| Ph | 7-10 |
| Intensity | 1,30±0,2g/cm ³ |

PERFORMANCE

(23°C, 50% Relative Humidity)

| | | |
|----------------------|-----|---------------------|
| Brightness | G3 | TS 4318 EN ISO 2813 |
| Grain Size | S 1 | TS 2620 EN ISO 1524 |
| Water Vapor Transfer | V 1 | TS EN ISO 7783-2 |
| Water Transfer Rate | W2 | TS EN 1062-3 |
| Dry Film Thickness | E 3 | TS EN 1062-1 |

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

USAGE AREAS

On exterior facades; It is used on cement-based plaster, concrete, etc. surfaces primed with PROTHERM PRIMER and PROFACADE PRIMER.

Silicone Exterior Paint

APPLICATION INSTRUCTIONS

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. The surface should be rough. If there are significant defects on the application surface, they should be repaired with PROREPAIR repair mortar at least 24 hours in advance.

PROCOLOR EXT Exterior Paint is mixed with 10 - 15% water using a low speed mixer.

Application Equipment

hand mixer - Roll

It is applied in two layers to the surface primed with exterior primer 24 hours before.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application should not be made on surfaces at risk of frost. The product should be protected from rain, water, frost and negative external factors until it is cured.

CONSUMPTION

7-9 m² / It in a single coat, depending on the absorbency of the surface

PACKAGING

15 lt plastik bucket

SHELF LIFE

It is valid for 1 year from the date of production in its original packaging with the lid closed, in a dry and moisture-free environment without direct sunlight, at a temperature of +5 - 25 C and 50% relative humidity. The lids of the packages should be closed tightly when not in use. It should be kept away from moisture. Protect from high temperatures and frost.

STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). It should not be left under direct sunlight.

990 PROCOLOR EXT



Silicone Exterior Paint

SAFETY

Do not inhale the product and do not contact it with skin or eyes. Use protective gloves, glasses and clothing. In case of eye contact, rinse with plenty of water and consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com