

415 PROCERA FL



Cement Based Large Size Ceramic Adhesive Mortar C1TE

PRODUCT DESCRIPTION

It is a normally hardening, cement-based, large-sized ceramic adhesive mortar with reduced slip properties.

FEATURES

It is resistant to water, moisture and impacts.

It is resistant to surface tension.

Its suitable setting time provides ease of application and does not require much labor.

It has high adhesion strength.

It has high adherence.

It is suitable for ceramic flooring from top to bottom and horizontally.

It can be easily combed.

PRODUCT INFORMATION

Chemical structure	: Cement Based
Appearance/Color	: Powder / Gray
Pot life	: 30 Min
C	: Cement Based
1	: normal adhesive
T	: Reduced slip ability
E	: Extended Open Time

PERFORMANCE:

(23°C, 50% Relative Humidity)

Tensile Adhesion	0,5 N/mm ²	TS EN 1348
Tensile Adhesion After Water	0,5 N/mm ²	TS EN 1348
Shrinkage Adhesion After Heat	0,5 N/mm ²	TS EN 1348
Shrinkage Adhesion After Freezing	0,5 N/mm ²	TS EN 1348
Open Hold Time: 30 minutes later	0,5 N/mm ²	TS EN 1346
Slip Determination	<0,5 mm	

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

USAGE AREAS

For bonding covering materials such as ceramics, tiles, mosaics, decorative bricks, natural stones; It can be applied on surfaces such as concrete, brick and plaster in wet areas such as bathrooms and kitchens. Before applying ceramic on existing ceramic, the surface must be roughened with PROJEL PR.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

415 PROCERA FL



Cement Based Large Size Ceramic Adhesive Mortar C1TE

Application Equipment

Hand mixer - Trowel - Plastic hammer - Notched trowel .

APPLICATION INSTRUCTIONS

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. The surface should be rough. If there are significant defects on the application surface, they should be repaired with PROREPAIR repair mortar at least 24 hours in advance.

Slowly pour 25 kg of BARS PROCERA FL onto 6-7 liters of water and mix with a low speed mixer until no lumps remain. The mortar is left to rest for 5-6 minutes to mature. It is mixed again before application. The prepared mortar is spread on the surface with a trowel. It is scanned by moving it in a circular motion with a notched trowel. Ceramics are adhered to the combed mortar by pressing. Joint fillers can be used between ceramics to ensure an equal share of joint filler. Expired or encrusted mortar in the container should be disposed of. The surface should be cleaned with a damp cloth. Direct contact of the adhered tiles with water and pedestrian traffic should be avoided for at least 24 hours.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application should not be made on surfaces at risk of frost. The product should be protected from rain, water, frost and negative external factors until it is cured.

CONSUMPTION

3-5 kg/m²

PACKAGING

In a 25 kg kraft bag, (64 pieces on a pallet, 1600 kg)

SHELF LIFE

It is 1 year from the date of production in its original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +35 C). The mouth of the containers should be tightly closed when not in use. Should be kept away from moisture .

STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +35 C). Should not be left in direct sunlight .



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

415 PROCERA FL



Cement Based Large Size Ceramic Adhesive Mortar C1TE

SAFETY

Since it is cement based, do not breathe the dust and do not contact it with skin or eyes. Use mask. Use protective gloves, glasses and clothing. In case of eye contact, consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com