

# 496 PROPOLY MASTIC



## *Polyester Resin Based Two Component Granite Marble Adhesive*

### PRODUCT DESCRIPTION

It is a polyester resin based, two component marble adhesive mastic.

### FEATURES

It is resistant to water, moisture and impacts.

It is easy to sand.

It fills the pores.

It has maximum performance.

It is thixotropic.

It has high adhesion strength.

It has high adherence.

It is suitable for ceramic flooring from top to bottom. It can be combed easily.

### PRODUCT INFORMATION

#### Mastik

Chemical structure : Polyester resin based  
Appearance/Color : Liquid / cream & beige & white&black

#### Hardener:

Chemical structure : Dibenzoilperoksit pasta  
Appearance/Color : Liquid / White

### PERFORMANCE

(23°C, 50% Relative Humidity)

Tensile Adhesion Intensity	1,34±0,2 N/mm <sup>2</sup> 1,7±0,2 gr/cm <sup>3</sup>	TS EN 196-1
----------------------------	--	-------------

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. Values may change due to differences in temperature and humidity in the construction site environment. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

### USAGE AREAS

It is used for adhesion of coating materials such as ceramics, tiles, marble, natural stone, and in repair and filling operations.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 496 PROPOLY MASTIC



*Polyester Resin Based  
Two Component Granite Marble Adhesive*

## APPLICATION INSTRUCTIONS

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. The surface should be rough.

Approximately 1-3% by weight of propoly mastic and 50% dibenzoyl peroxide paste are added and mixed thoroughly with the help of a spatula. It is applied. It hardens within 5-8 minutes at 20°C. The bonded surfaces are ready for use 2 hours after application. Excessive addition of hardener accelerates curing but may cause a decrease in adhesion strength. Do a small trial for optimum results.

## LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application should not be made on surfaces at risk of frost. Keep the lid of the glue container closed after use.

## PACKAGING

Mastic: 750 ml tin

## SHELF LIFE

It is 6 months from the date of production in its original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). The mouth of the containers should be tightly closed when not in use. Should be kept away from moisture

## STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). It should not be left under direct sunlight.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 496 PROPOLY MASTIC



**Polyester Resin Based  
Two Component Granite Marble Adhesive**

## SAFETY

Do not inhale the product and do not contact it with skin or eyes. Use mask. Use protective gloves, glasses and clothing. In case of eye contact, consult a doctor immediately. Make sure the place is well ventilated during use. Keep out of reach of children. Do not swallow. Keep away from flammable materials. For detailed information and recommendations, please refer to the Safety Data Sheet.

## LEGAL NOTES

*Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.*

*DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.*

*DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.*



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE  
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com