

# 497 PROMARBLE ULTRA MAX W



## **Cement Based High Performance Ultra Flexible Granite and Marble Adhesive Mortar - White C2TE S2**

### **PRODUCT DESCRIPTION**

It is a cement-based, high-performance, ultra-flexible, reduced-slip, deformable, waterproofing adhesive mortar for all sizes of ceramics, marbles and granites.

### **FEATURES**

It is patent and yellowish in color.

It is ultra flexible and adheres to all sizes.

It is used vertically and horizontally on interior and exterior facades.

Provides waterproofing in double-sided applications

Provides sound insulation between floors thanks to its special components

It is resistant to water, moisture and impacts.

It has maximum performance.

It provides ease of application with its foamy light structure and does not require much labor.

It has high adhesion strength. Its adherence is very high.

It is suitable for ceramic flooring from top to bottom. It can be combed easily.

### **PRODUCT INFORMATION**

Chemical structure :	Cement Polymer based
Appearance/Color :	Powder / Orange
Pot Life :	1 Hrs
C :	cement based
2 :	High Performance Adhesive
T :	Reduced slip ability
E :	Extended Open Time
S2 :	Can be deformed

### **PERFORMANCE**

(23°C, 50% Relative Humidity)

Pot Life	6 Hrs
Tensile Adhesion	1 N/mm <sup>2</sup>
Tensile Adhesion After Water	1 N/mm <sup>2</sup>
Shrinkage Adhesion After Heat	1 N/mm <sup>2</sup>
Shrinkage Adhesion After Freezing	1 N/mm <sup>2</sup>
Open Hold Time: 30 minutes later	1 N/mm <sup>2</sup>
Flexibility (EN 12002)	5 mm - VERY FLEXIBLE
Slip Determination	< 0,5 mm
temperature resistance	-40 +80

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. Values may change due to differences in temperature and humidity in the construction site environment. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 497 PROMARBLE ULTRA MAX W



***Cement Based High Performance Ultra Flexible Granite  
and Marble Adhesive Mortar - White C2TE S2***

## USAGE AREAS

For bonding coating materials such as ceramics, tiles, marble, granite, natural granite, mosaic, decorative brick, natural stone; It can be applied in wet areas such as bathrooms and kitchens, and on surfaces such as concrete, brick and plaster. Before applying ceramic on existing ceramic, the surface must be roughened with PROJEL.

## APPLICATION EQUIPMENT

Hand mixer-Twelve-Plastichammer-Gearmala

## APPLICATION INSTRUCTIONS

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. The surface should be rough. If there are significant defects on the application surface, they should be repaired with PROREPAIR repair mortar at least 24 hours in advance.

Slowly pour 20 kg of PROMARBLE ULTRA 500 onto approximately 5 liters of water (consistency is determined by the product and the ground) and mix with a low-speed mixer until there are no lumps left. The mortar is left to rest for 5-10 minutes to mature. It is mixed again before application.

PROMARBLE ULTR A MAX is spread on the surface with a trowel. It is combed by moving it in a circular motion with a notched trowel, the bottom of the ceramic is wiped with a damp cloth before adhesion, and the ceramics are adhered by pressing on the mortar that is notched under the ceramic with a flat steel trowel. Joint fillers can be used between ceramics to ensure equal grout share. Expired or encrusted mortar in the container should be disposed of. Surfaces should be cleaned with a damp cloth.

Direct contact of the adhered tiles with water should be avoided for at least 24 hours.

## LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application should not be made on surfaces at risk of frost. The product should be protected from rain, water, frost and negative external factors until it is cured.

## CONSUMPTION

4-6 kg/m<sup>2</sup>

## PACKAGING

In a 20 kg kraft bag, (64 pieces on a pallet, 1280 kg)



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE  
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 497 PROMARBLE ULTRA MAX W



## **Cement Based High Performance Ultra Flexible Granite and Marble Adhesive Mortar - White C2TE S2**

### **SHELF LIFE**

It is 1 year from the date of production in its original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +35 C). The mouth of the containers should be tightly closed when not in use. It should be kept away from moisture.

### **STORAGE CONDITIONS**

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +35 C). It should not be left under direct sunlight.

### **SAFETY**

Since it is cement based, do not breathe the dust and do not contact it with skin or eyes. Use mask. Use protective gloves, glasses and clothing. In case of eye contact, consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

### **LEGAL NOTES**

*Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.*

*DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.*

*DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.*



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE  
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com