

# 530 PROGROUT SPEED



## **Cement Based High Strength Fast Setting Grout Mortar**

### **PRODUCT DESCRIPTION**

It is a cement-based, high-strength, fast-setting, non-shrinking, fluid polymer-modified grout mortar.

### **FEATURES**

It sets quickly. It is fluid and saves time and labor. It is easy to apply.

It does not cause shrinkage shrinkage cracks. It has high abrasion resistance. Protects steel reinforcement against corrosion.

### **PRODUCT INFORMATION**

Chemical structure : Cement Based  
Appearance/Color : Powder/Gray

### **PERFORMANCE**

(23°C, 50% Relative Humidity)

Void Unit Volume Mass of Fresh Mortar	1350 ± 200 kg/m <sup>3</sup>	TS EN 1015-6
Compressive Strength 28 days	55 N/mm <sup>2</sup>	TS EN 1015-11
Flexural Strength 28 days	8 N/mm <sup>2</sup>	TS EN 1015-11
Capillary Capillary Water Absorption	0,5 gr	TS EN 1015-18
Application thickness	10mm - 75 mm	

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

### **USAGE AREAS**

It is used in fixing steel columns to the foundation, in the assembly of machine foundations, in the assembly, repair and elevation of manhole beds, in concrete repair, in the fixing of turbines in WPP power plants, in the repair of concrete floors exposed to traffic, in the assembly of prefabricated concrete structural elements, in the repair of paving stones, in the repair of fractures in concrete floors and in filling the gaps.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 530 PROGROUT SPEED



## **Cement Based High Strength Fast Setting Grout Mortar**

### **APPLICATION EQUIPMENT**

Hand mixer - Steel Trowel - Iron rod

### **APPLICATION INSTRUCTIONS**

Surface; It must be cured, dry and sound. It should be cleaned of any residues such as oil, grease, dirt, paint, salt vomit that would prevent adhesion. The surface must be roughened. If there is rust on the metal reinforcement, it should be removed. Formworks must be securely fixed. Tightness should be checked by filling with water. If the application will be made on old concrete, the surface must be moistened before application. Concrete must be saturated with water. Puddles of water should be avoided. Slowly pour 25 kg of PROGROUT SPEED into 3-4 liters of water and mix with a low-speed mixer until no lumps remain. Application should be started immediately as it will set quickly.

A mold is made where the casting will be made. The mold should be mounted in a way to prevent water leakage. The mold must be filled from one side without interruption, thus preventing air formation inside the mold. Air bubbles that may form prevent surface contact and weaken adherence. Since it sets quickly, the prepared mortar should be applied without waiting. The mortar is allowed to settle by tamping it with an iron rod. Due to the expansion feature of the product, it is recommended to complete the process within 3-5 minutes at most in order to benefit from it at the highest level. Expired mortar should be disposed of.

### **LIMITATIONS**

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C. Application should not be made in hot, rainy and windy weather. Application should not be made on surfaces at risk of frost. The product should be protected from rain, water, frost and negative external factors until it is cured.

### **CONSUMPTION**

1.5-2 kg/m<sup>2</sup> (for 1 mm layer thickness)

### **PACKAGING**

In a 25 kg kraft bag, (64 pieces on a pallet, 1600 kg)

### **SHELF LIFE**

It is 1 year from the date of production in its original packaging in moisture-free and dry environments (temperature between +5 C and +35 C). The mouth of the containers should be tightly closed when not in use. It should be kept away from moisture.

### **STORAGE CONDITIONS**

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +35 C). It should not be left under direct sunlight.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com

# 530 PROGROUT SPEED



## Cement Based High Strength Fast Setting Grout Mortar

### SAFETY

Since it is cement based, do not breathe the dust, use a mask. Avoid contact with skin and eyes. Use protective gloves, glasses and clothing. In case of eye contact, consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

### LEGAL NOTES

*Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.*

*DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.*

*DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.*



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti  
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78  
Gürsu /BURSA TÜRKİYE  
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01  
www.barskimya.com info@barskimya.com