

1010 PROCONCRETE



Cement Based Decorative Castina Mortar

PRODUCT DESCRIPTION

Cement-based, self-leveling, suitable for use in silicone molds for decorative flower pots, figurines, sculptures, etc. It is a fast-drying casting mortar for products.

FEATURES

Smooth results are achieved.

Candle holders, candlesticks, flower pots, bowls, vases and many other decorative objects can be made.

It can be painted after it dries.

PRODUCT INFORMATION

Chemical Structure : Cement Based

Appearance / Color : Powder / Gray

PERFORMANSCE

(23°C, 50% Relative Humidity)

Start of setting : 5 min

End of socket : 10-15 min

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. Values may change as the temperature and humidity values in the environment and mold volumes will vary.

USAGE AREAS

It is suitable for use in silicone molds.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

1010 PROCONCRETE



**Cement Based
Decorative Casting Mortar**

APPLICATION INSTRUCTIONS

Clean your casting mold beforehand. The mold must be clean and dry. To make our concrete mortar, according to the size of the mold we will pour, 30% of the powdered product amount by mass is taken into a container. Add PROCONCRETE slowly while mixing. It is constantly mixed until it becomes homogeneous and smooth. The prepared concrete mixture is poured into the mold within 3-5 minutes before it hardens. Our concrete will dry after 15-20 minutes, but for best results, it is recommended to remove it from the mold the next day. Drying time may vary depending on weather conditions and mold. It is recommended to remove it from the mold after 24 hours.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should be made between +5 C and +30 C.

PACKAGING

3 kg plastic bucket
10 kg plastic bucket

SHELF LIFE

It is 6 months from the date of production in its original packaging in moisture-free and dry environments (temperature between +5 C and +35 C). The mouth of the containers should be tightly closed when not in use. It should be kept away from moisture.

STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +35 C). It should not be left under direct sunlight.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

1010 PROCONCRETE



Cement Based Decorative Casting Mortar

SAFETY

Since it is cement based, do not breathe the dust and do not contact it with skin or eyes. Use protective gloves, glasses and clothing. In case of eye contact, consult a doctor immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE
Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com