

605 PROXY PLUS



Industrial Primer Paint

PRODUCT DESCRIPTION

It is an alkyd resin based, air drying primer used for industrial purposes.

FEATURES

Dries quickly. It is a primer paint containing anticorrosive pigments. It does not cause brush marks or bleeding. It adheres well to metal surfaces. It creates a smooth surface for industrial topcoat paint. It is resistant to impacts and short-term diluted chemicals.

PRODUCT INFORMATION

Chemical Structure : Alkyd Based / Solvent Based

Appearance / Color : Liquid / RAL Chart

PERFORMANSCE

(23°C, 50% Relative Humidity)

Intensity	1,30 ±0,2 gr / cm ³
Solid Part	(% by weight) 66 ± 2 ASTM D-1353
Drying Times	
Dust-free drying	20-30 Min
touch dry	2-3 Hours
complete drying	24 Hours

These values were obtained as a result of laboratory experiments carried out in our company and are valid for the performance of finished applications at the end of the full drying period. The values may change as the temperature and humidity values in the construction site environment and the application surfaces and areas will vary.

USAGE AREAS

It is used for painting all kinds of metal, pipes and profiles.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

605 PROXY PLUS



Industrial Primer Paint

APPLICATION EQUIPMENT

Hand mixer - Roller - Spraying Equipment

APPLICATION INSTRUCTIONS

The surfaces to be applied should be free from all kinds of oil, dirt, etc. that will reduce adherence. The substance must be cleared. Metal surfaces should be sandblasted to at least Sa2 ½ degree, which is the ideal method, and should be primed with Industrial Primer or Rapid Primer within 6 hours. After the primer has dried (2 hours later), the final coat application can be started. The surface temperature must be at least 10°C. It should not be applied to wet or damp surfaces near the dew point.

It can be thinned by 10 - 15% with thinner.

LIMITATIONS

To obtain optimum quality, please adhere to the application instructions. Application should not be made in very high temperatures, direct exposure to sunlight, very windy or rainy weather. Application should not be made on surfaces that are at risk of frost at the time of application. Application should be made between +5 C and +30 C. Application should never be made at temperatures below 5 C. After application, it should be protected from rain, water, frost and negative external factors for 24 hours.

CONSUMPTION

120 gr/m², variable depending on surface roughness and application method

PACKAGING

5 kg tin packaging

15 kg tin packaging

SHELF LIFE

It is 1 year from the date of production in its original packaging in moisture-free and dry environments (temperature between +5 C and +25 C). The mouth of the containers should be tightly closed when not in use. It should be kept away from moisture.

STORAGE CONDITIONS

It should be stored in its unopened original packaging in a moisture-free, dry and cool environment (temperature between +5 C and +25 C). It should not be left under direct sunlight.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com

605 PROXY PLUS



Industrial Primer Paint

SAFETY

Avoid contact with skin and eyes. Use protective gloves, glasses, mask and clothing. In case of eye contact, consult a doctor immediately. Keep out of reach of children. Avoid skin contact. For detailed information and recommendations, please refer to the Safety Data Sheet.

LEGAL NOTES

Our technical data sheet is DEKOSTAR LTD., which has a wide range of usage areas. ŞTİ. It has been prepared to give general information about the products and to show the technical features of the products. It is a recommendation and this information is about the correct application, ground, air, equipment, etc. It is valid under the conditions and when the products are stored under the recommended conditions.

DEKOSTAR LTD. ŞTİ. Since it cannot control the conditions under which its products are used, it does not accept any responsibility for the application result and does not guarantee it. The user of the product must test the suitability of the product before using it.

DEKOSTAR San. will be liable for application errors that may occur if the product is used for purposes other than its intended purpose or if the application conditions and recommendations stated above are not followed. and Tic. Ltd. Ltd. is not responsible and has the right to change the features of its products without notice. Users should always refer to the latest edition of the Product Technical Data Sheet for the relevant product.



BARS KİMYA -Dekostar Yalıtım İnşaat San. ve Tic.Ltd.Şti
Gürsu Yeni Sanayi Alanı Karahıdır Mah. Okul Yolu Üzeri No:78
Gürsu /BURSA TÜRKİYE

Tel : (+90) 850 888 61 00 Whatsapp Gsm : (+90) 516 168 61 01
www.barskimya.com info@barskimya.com